

CONFIDENTIAL **CONFIDENTIAL**

- 2 -

*Non-metallic rating based on micro-examination reported in Paragraph 3 below.

3. The heat treating of the 2GLZ bearing was unacceptable by USA standards, and the count of non-metallic inclusions (principally oxide and manganese sulphide stringers) was sub-standard for all parts of this bearing.

Available from the CIA Library are photomicrographs of bearings 1 and 2 and bearing 2GLZ as follows: (a) Photomicrographs at 1000 diameters etched with Vilella's Reagent to show grain size; (b) Photomicrographs at 100 diameters, metal etched, to show structure; (c) Photomicrographs at 100 diameters unetched to show non-metallic inclusions.

4. The chemical analyses of bearings 1, 2 and 2GLZ are reported as follows:

	<u>Bearing 1</u>				<u>Bearing 2</u>				<u>2GLZ</u>			
	Inner	Outer	Balls	Ret.	Inner	Outer	Balls	Ret.	Inner	Outer	Balls	Ret.
Carbon	1.05	1.04	1.06	.09	1.06	1.02	.96	.07	.96	1.01	1.07	.11
Manganese	.37	.32	.33	.39	.35	.36	.37	.39	.29	.36	.28	.32
Phosphorous												
Sulphur												
Silicon												
Chromium	1.51	1.46	1.38		1.47	1.43	1.38		1.62	1.63	.62	
Nickel	.10	.23	.21		.08	.22	.25		.18	.22	.11	
Copper	.06	.12	.13		.06	.09	.13		.24	.20	.20	
Molybdenum	.02	.05	.03		.01	.06	.04		.03	.03	.01	

5. Conclusions drawn from these and former analyses of Soviet bearing 2GLZ are as follows:
- Bearing 2GLZ outlasts comparable American bearings under identical test conditions by more than 3 to 1.
 - Soviet bearing 2GLZ shows evidence of dimensional control, heat treating, and non-metallic contamination which may be deliberately engineered to produce a product just good enough to do the intended job.
 - The chemical composition of bearing 2GLZ is conventional but somewhat high in copper.
 - Bearing 2GLZ shows unexpectedly small grain size in the inner race.

- end -

CONFIDENTIAL

CONFIDENTIAL

CONFIDENTIAL

3/21/50 RETURN TO CIA
LIBRARY

Appendix

X1000 Etched with Vilella's Reagent

Photo #5206




Figure 1
SKF #1 Inner

Photo #5203



Figure 2
"X" Inner (FGS-6 $\frac{1}{4}$)

Photo #5207




Figure 3
SKF #2 Outer

Photo #5204




Figure 4
"X" Outer

CONFIDENTIAL

25X1A

3/21/51

X100

Nital Etch

Photo #5208




Figure 5
SKP #1 Retainer

Photo #5205




Figure 6
"X" Retainer

25X1A

3/21/51


RETURN TO CIA

Photo #5119
"X" Outer Ring




Rating #4

Photo #5121
"X" Inner Ring



Rating #3

Photo #5120
"X" Ball



Rating #3


CONFIDENTIAL

5/21/51


Non-Metallic Inclusion Rating 100X No Etch

Photo #5216
SKF #2 Outer Ring

Photo #5117
SKF #2 Inner Ring




Rating #3



Rating #3

Photo #5118
SKF #2 Ball




RETURN TO CIA
LIBRARY

3/21/51


Photo #5122
SKF #1 Inner

Photo #5123
SKF #1 Ball



Rating #4

25X1A



Rating #4

Comments

The SKF #2 bearing parts showed manganese sulphides, large oxide and small silicate-type inclusions. However, the outer and inner would be just acceptable according to our standards. The ball would be considered objectionable because of the small chain-type silicate inclusions.

The "X" bearing parts would be all rejected according to our standards. The type of inclusions are oxide and manganese sulphide stringers.

The SKF #1 bearing parts would also be rejected according to our standards.

The inclusions are mostly all of the long oxide stringer type.

25X1A

RETURN TO CIA
LIBRARY

CONFIDENTIAL